



TESTING SERVICES, INC.
 817 SHOWALTER AVE. • P.O. BOX 2041
 DALTON, GEORGIA 30722-2041
 PHONE: (706) 226-1400 • FAX: (706) 226-6118



Mondo America Testing Summary

CLIENT:	Mondo America Inc.	REPORT NUMBER:	43530RR
	2655 Francis Hughes	LAB TEST NUMBER:	1999-5669
	Laval, Quebec, CN H7L 3S8	DATE:	March 23, 2009

TEST MATERIAL:

Turf ID
Mondoturf PF-3250 DL

OVERVIEW:

A synthetic turf sample was submitted for a battery of testing to analyze construction and physical properties.

TEST METHOD(S):

ASTM F1551: Standard Test Method for Comprehensive Characterization of Synthetic Turf Playing Surfaces and Materials

- ASTM D5848: *Standard Test Method for Mass Per Unit Area of Pile Yarn Floor Coverings (Construction Analysis)*
- ASTM D5823: *Standard Test Method for Tuft Height of Pile Floor Coverings*
- ASTM D789: *Standard Test Method for Determination of Relative Viscosity and Moisture Content of Poyamide (Melt Point)*
- ASTM D1577: *Standard Test Method for Linear Density of Textile Fibers (Denier)*
- ASTM D1335: *Standard Test Method for Tuft Bind of Pile Floor Coverings*
- ASTM D5034: *Standard Test Method for Breaking Strength of Textile Fabrics (Grab Test)*
- ASTM D5034: *Standard Test Method for Breaking Strength and Elongation of Textile Fabrics)*
- ASTM D3218: *Standard Test Method for Specification of Polyolefin Monofilaments*

TEST RESULTS:

Test Performed	Test Result	
Total Weight	71.77 oz/sy ²	
Pile Weight	33.05 oz/sy ²	
Primary Backing	8.70 oz/sy ²	
Secondary Backing	30.02 oz/sy ²	
Average Pile Height	1.98"	
Average Tuft Bind Strength	10.72 lbs/force	
Average Grab Tear Strength	(MD) 340.9 lbs/force	(CMD) 245.1 lbs/force
Breaking Strength	28.86 lbs/force	
Elongation	37.6 %	
Denier	7,837	
Ribbon Thickness	.00378"	96 microns
Melt Point	119°C Polyethylene	

Approved By:

 Erle Miles, Jr. VP
 Testing Services Inc.