

SUPER X PERFORMANCE 08 mm

Revision # 0 of 04/20/09

Product Description	Prefabricated athletic rubber flooring. Designed specifically for track & field applications. Designed for interior and exterior applications. Composed of natural and synthetic rubbers, mineral fillers, vulcanizing and stabilizing agents and color pigments. Manufactured in two layers, which are calandered and vulcanized together. The top layer is embossed. It provides surface drainage, slip-resistance, spike-resistance, elasticity, foot traction and durability. The bottom layer consists of a deformable geometric construction that provides high cushioning and energy return. The shore hardness of the top layer is greater than that of the bottom layer.		
Surface Texture	Track Embossing		
Surface Color	Please refer to Mondo's website for available colors		
Tile Size	N/A		
Roll Width	3' to 6' (0.92m to 1.83m)		
Roll Length (Width between 3' and 5')	49' (min. 10' / max 52') - 15m (min. 3m / max 16m)		
Roll Length (Width between 5' and 6')	39' (min. 10' / max 42') - 12m (min. 3m / max 13m)		
Adhesive	Mondo PU100 Regular	Outdoor applications with night temperatures equal to or above 50 °F	
	Mondo PU100 Fast Set	Outdoor applications with night temperatures between 40 °F and 50 °F . Special restrictions and installation procedures apply. Please contact Mondo's Technical Department prior to placing any order.	
	Mondo PU 105	Indoor applications only	
	Mondo EP 55	Indoor application on concrete subfloors only; not suitable for installation over Everlay; not suitable for heavy impact loads	
Subfloor Preparation	Please refer to Mondo's Subfloor Preparation Guidelines		
Installation	Please refer to Mondo's Sportflex & Super X Indoor Installation Manual		
Maintenance	Please refer to Mondo's Sportflex & Super X Maintenance Manual		
L.E.E.D. ® Contributions			
Regional Materials	Manufactured in Laval, Quebec, Canada		
Post-Consumer Recycled Content	0% by weight	0.00 lbs/sqft	0.00 Kg/sqm
Pre-Consumer Recycled Content	36% by weight	0.55 lbs/sqft	2.70 Kg/sqm
Rapidly Renewable Materials Content	12% by weight	0.18 lbs/sqft	0.87 Kg/sqm
Technical Data	Test Method	Unit	Average Values
Thickness	-	mm	8 ± 0.2
Weight	-	Kg/m ²	7.5 ± 5%
Tensile Strenght	ASTM D412-06	psi	≥ 120
Elongation at Break	ASTM D412-06	%	≥ 130
Hardness of Top Layer	ASTM D2240-05	Shore "A"	50 ± 5
Hardness of Bottom Layer	ASTM D2240-05	Shore "A"	40 ± 5
Abrasion Resistance Taber (H18 Wheel 1000 cycles 1000g load)	ASTM D3389-05	gr weight loss	≤ 2
Static Load Limit (250 Lbs)	ASTM F970-06	Inches	≤ 0.007
Coefficient of Friction* ¹	ASTM D2047-04	-	Dry ≥ 1.0 / Wet ≥ 1.0
Fungal Resistance Test	ASTM G21-96	-	No Growth
Chemical Resistance	ASTM F925-02	-	No Surface Attack
Critical Radiant Flux	ASTM E 648-06	W/cm ²	≥ 0.45 Class 1
Optical Smoke Density	ASTM E662-06	-	< 450
Spike Resistance	UNI EN 14810	ΔTr %	≤ 20
		ΔEb %	≤ 20
Notes	* ¹ OSHA Requires Coefficient of Friction > 0.5 ADA Requires Coefficient of Friction > 0.6 for Flat Surfaces, > 0.8 for Ramps		