

# ASTM E 2180 – 18

*Standard Test Method for Determining the Activity of Incorporated Antimicrobial Agent(s) in Polymeric or Hydrophobic Materials*

*FINAL REPORT: R2019-303*

Prepared for:  
Mondo  
2655 Francis-Hughes  
Laval, QC H7L 3S8

*Accredited Testing Provided by:*



130 Erick Street  
Crystal Lake, IL 60014  
815.526.0954  
TESTING CERT: #2832.01

*Testing Initiated: June 26, 2019*

*Testing Completed: July 1, 2019*

*Report Issued: July 3, 2019*

Performed By: Marcy Aaron  
Title: Staff Scientist

Approved By: Debbie Koester  
Title: Quality Manager



**Objective:**

To evaluate the surface of one sample for antimicrobial effectiveness against *Methicillin-resistant Staphylococcus aureus (MRSA) ATCC# 43300* as demonstrated by ASTM E 2180 test method.

**Test Sample Identification:**

1. Mondo Sport Impact

**Test Procedure Summary:**

The test organism was adjusted and diluted to obtain the starting inoculum concentration in an agar slurry. The control was tested in triplicate at Time = 0 and Time = 24 hours. The test samples were tested in triplicate at Time = 24 hours. Each replicate was placed in a sterile Petri dish, inoculated and then incubated. At the appropriate time, the replicate was placed in sterile container with neutralizing broth and shaken to facilitate the release of the agar slurry to the neutralizing broth. Serial dilutions of the neutralizing broth containing the inoculum were plated. All plates were incubated. After incubation, bacterial colonies were counted and recorded. The results are found in the Test Results section. The results pertain only to the samples tested.

**Test Variables**

<b>Test Organism:</b>	<i>Methicillin-resistant Staphylococcus aureus (MRSA) ATCC# 43300</i>
<b>Sample Size:</b>	3cm x 3cm
<b>Pre-Cleaning:</b>	None
<b>Control:</b>	Untreated plastic control supplied by MicroStar
<b>Neutralizing Broth Used:</b>	10 mL D/E Neutralizing Broth
<b>Starting Inoculum Concentration:</b>	<i>S. aureus (MRSA) ATCC# 43300</i> : 4.3 x 10 <sup>6</sup> ; Log value 6.63
<b>Amount of Inoculum:</b>	1.0 mL
<b>Contact Time:</b>	24 hours
<b>Deviations from Standard Test Method:</b>	None, testing performed per ASTM E2180 without deviation.



**Test Results:**

Log reduction and percent reduction is determined by comparing the treated sample after the contact time to the untreated plastic control after the contact time using the geometric mean (average of log values of each replicate) and antilog as indicated by the standard test method. The average number of recovered bacteria and log reduction are reported as Log<sub>10</sub> values.

**Results against *S. aureus* (MRSA) ATCC# 43300 after 24-hour Contact Time**

<b>Sample</b>	<b>Geometric Mean of Recovered Bacteria</b>	<b>Log Reduction</b>	<b>Percent Reduction</b>
Untreated Plastic Control	6.44		
Mondo Sport Impact	1.70	4.74	99.998

Percent reduction is translated into log reduction by the following:

90% reduction = 1 log reduction; i.e. 1,000,000 (Log Value 6.00) reduced to 100,000 (Log Value 5.00)

99% reduction = 2 log reduction; i.e. 1,000,000 (Log Value 6.00) reduced to 10,000 (Log Value 4.00)

99.9% reduction = 3 log reduction; i.e. 1,000,000 (Log Value 6.00) reduced to 1,000 (Log Value 3.00)

99.99% reduction = 4 log reduction; i.e. 1,000,000 (Log Value 6.00) reduced to 100 (Log Value 2.00)

99.999% reduction = 5 log reduction; i.e. 1,000,000 (Log Value 6.00) reduced to 10 (Log Value 1.00)

The detection limit for this test is log<sub>10</sub> value 1.00 due to the 10x dilution that occurs with the addition of the neutralizing broth. Results reported as <1.00 means there were no test organisms found on the lowest dilution plate.