

ISO 22196: 2011(E)

PLASTICS – MEASUREMENT OF ANTIBACTERIAL ACTIVITY ON PLASTICS AND OTHER NON-POROUS SURFACES

FINAL REPORT: R2019-302

Prepared for:
Mondo
2655 Francis-Hughes
Laval, QC H7L 3S8

Accredited Testing Provided by:



130 Erick Street
Crystal Lake, IL 60014
815.526.0954
TESTING CERT: #2832.01

Testing Initiated: June 26, 2019
Testing Completed: July 1, 2019
Report Issued: July 3, 2019

Performed By: Marcy Aaron
Title: Staff Scientist

Approved By: Debbie Koester
Title: Quality Manager



Objective:

To evaluate the antibacterial activity on the surface of one sample as demonstrated by the ISO 22196:2011(E) test method.

Test Sample Identification:

1. Mondo Sport Impact

Test Procedure Summary:

The test organism was adjusted and diluted to obtain the starting inoculum concentration of 2.5-10 x 10⁵ CFU/mL. The control was tested in triplicate at Time = 0 and Time = 24 hours. The test samples were tested in triplicate at Time = 24 hours. Each sample piece was placed in a sterile Petri dish, inoculated and then covered with the sterile plastic in order to spread the inoculum evenly over the sample surface and hold it in place. The samples were incubated at 35°C and a relative humidity of at least 90%. At the appropriate time the neutralizing broth was added to each sample, placed onto a shaker and mixed thoroughly to facilitate the release of the inoculum from the sample surface. Serial dilutions of the neutralizing broth containing the inoculum were plated. All plates were incubated at 35°C for 24-48 hours. After incubation, bacterial colonies were counted and recorded. The results are found in the “Test Results” section below. These results pertain only to the samples tested.

Test Variables

Test Organism:	<i>Methicillin-resistant Staphylococcus aureus (MRSA)</i> ATCC# 43300
Sample Size:	50 mm x 50 mm
Method of Sterilization /Pre-Cleaning:	None
Control Sample:	Untreated plastic control supplied by MicroStar
Film Used:	40 mm x 40 mm x 0.05 mm plastic pieces cut from sterile Whirlpak™ bags
Dilution Medium Used:	Sterile dilute nutrient broth per standard
Neutralizing Broth Used:	D/E Neutralizing Broth
Amount of Neutralizing Broth:	10 mL
Starting Inoculum Concentration:	<i>S. aureus (MRSA) ATCC# 43300</i> : 4.6 x 10 ⁵
Amount of Inoculum:	0.4 mL
Contact Time:	24 hours
Deviations from Standard Test Method:	None, testing performed per ISO 22196 without deviation.



Test Results:

Results against *S. aureus* (MRSA) ATCC#43300:

Untreated Control	U_0 : Average of logarithm numbers of viable bacteria at Time = 0	4.23
Untreated Control	U_t : Average of logarithm numbers of viable bacteria at Time = 24 h	5.32
Mondo Sport Impact	A_t : Average of logarithm numbers of viable bacteria at Time = 24 h	-0.20

<u>Sample</u>	<u>Value of Antimicrobial Activity (R)</u>	<u>Percent Reduction</u>
Mondo Sport Impact	5.52	99.9997

Test Results Interpretation:

The value of the antimicrobial activity was calculated according to the formula listed below and recorded as log reduction.

$$R = (U_t - U_0) - (A_t - U_0) = U_t - A_t$$

Where,

R : antimicrobial activity

U_0 : average of logarithm numbers of viable bacteria from untreated plastic control at Time = 0 hour

U_t : average of logarithm numbers of viable bacteria from untreated plastic control at Time = 24 hour

A_t : average of logarithm numbers of viable bacteria from test sample at Time = 24 hour

According to the standard, an antibacterial product is determined to have antibacterial effectiveness when the antibacterial activity (R) is 2.0 or more.

Percent reductions are determined by comparing the sample after the contact time to the untreated plastic control after the contact. Reporting of percent reduction is not indicated by the test method but is provided by MicroStar as additional information.

Percent reduction is translated into log reduction by the following:

90% reduction = 1 log reduction; i.e. 1,000,000 reduced to 100,000 is a 1 log reduction

99% reduction = 2 log reduction; i.e. 1,000,000 reduced to 10,000 is a 2 log reduction

99.9% reduction = 3 log reduction; i.e. 1,000,000 reduced to 1,000 is a 3 log reduction

99.99% reduction = 4 log reduction; i.e. 1,000,000 reduced to 100 is a 4 log reduction

99.999% reduction = 5 log reduction; i.e. 1,000,000 reduced to 10 is a 5 log reduction