





Characteristic	Standard	Unit	Requirement***	Result*
Elongation at Break	ASTM D412	%	≥100	>160
Tensile Strength	ASTM D412	psi	≥75	>140
Hardness of Top Layer	ASTM D2240	Shore A	55 ±5	55 ±5
Hardness of Bottom Layer	ASTM D2240	Shore A	40 ±5	40 ±5
Abrasion Resistance (H18 wheels, 1000g, 1000 cycles)	ASTM D3389	g loss	≤2.0	≤1.2
Critical Radiant Flux	ASTM E648	W/cm ²	≥0.1	≥0.45 (Class 1)
Chemical Resistance**	ASTM F925	-	≤ Slight Change	Compliant
Resistance to Heat	ASTM F1514	ΔE	≤8.0	Compliant
Resistance to Light	ASTM F1515	ΔE	≤8.0	Compliant
Slip/Skid Resistance (Dry)	EN 13036-4	-	80-110	90
Slip/Skid Resistance (Wet)	EN 13036-4	-	55-110	79

Health and Environmental Attributes

Indoor Air Quality (VOC Emissions)	CA Section 01350	
	French Decree № 2011-321	
	GREENGUARD Certification	
	GREENGUARD Gold	
Materials and Resources (% by Weight)	Post-Consumer Recycled Content	≥42.5%
	Rapidly Renewable Materials	≥7%

Weight and Dimensions	Metric	Imperial
Thickness (ASTM F387)	13.5 mm (±0.3 mm)	0.531" (±0.011")
Weight	~13 kg/m ²	~2.66 lb/ft ²
Rubber Sheet Width	0.92 m to 1.50 m	3' to 4'11"
Rubber Sheet Length	15 m [min. 6 m; max. 16 m]	49'2" [min. 19'8"; max. 52'5"]

*Result from third-party testing can vary between production lots, laboratories and methods, and as such do not constitute representations or warranties as to any particular production lot. Mondo reserves the right to modify product design and/or specifications at any time without notice. **WARNING: RESULT OBTAINED FOR ANY FIRE SAFETY TESTING OR INDOOR AIR QUALITY CERTIFICATION ONLY APPLIES TO INDOOR INSTALLATIONS OVER CONCRETE AND MONDO INDOOR PRODUCTS DESIGNED FOR THIS PURPOSE.**

**For the complete list of chemicals tested, concentrations and contact time, please communicate with Mondo's Technical Department.

*****WARNING: MINIMAL REQUIREMENT TO BE RESPECTED AT ALL TIMES.**