

Characteristic	Standard	Unit	Requirement***	Result*
Static Coefficient of Friction (neolite heel)	ASTM D2047	-	≥0.50 (dry)	≥0.77 (dry)
Critical Radiant Flux	ASTM E648	W/cm ²	≥0.22 (Class 2)	≥0.45 (Class 1)
Flexibility (6 mm mandrel)	ASTM F137	-	No cracks/breaks	Compliant
Chemical Resistance	ASTM F925	-	≤Slight Change	Compliant**
Resistance to Heat	ASTM F1514	ΔE	≤8.0	Compliant
Resistance to Light	ASTM F1515	ΔE	≤8.0	Compliant
Force Reduction	ASTM F2772	%	≥22, ≤33 (Class 2)	Compliant
Vertical Deformation	ASTM F2772	mm	<1.8 (Class B)	Compliant
Ball Bounce	ASTM F2772	%	≥90.0	Compliant
Surface Finish Effect	ASTM F2772	BPV	80-110	Compliant

Health and Environmental Attributes

Indoor Air Quality (VOC Emissions)	ASTM D5116/CA Section 01350	
Ingredients	Vinylsport is manufactured <u>without</u> formaldehyde, lead or mercury.	
Manufacturing	Vinylsport is manufactured in an ISO 9001 and ISO 14001 certified facility.	

Weight and Dimensions	Metric	Imperial
Thickness (ASTM F386)	7 mm (±0.2 mm)	0.276" (±0.008")
Wear Layer Thickness (ISO 24340)	2 mm (±0.1)	0.079
Weight	~4.25 kg/m ²	~0.87 lb/ft ²
Sheet Width	1.80 m	5'10"
Sheet Length	20 m	65'7"

*Result from third-party testing can vary between production lots, laboratories and methods, and as such do not constitute representations or warranties as to any particular production lot. Mondo reserves the right to modify product design and/or specifications at any time without notice.

**For the complete list of chemicals tested, concentrations and contact time, please communicate with Mondo's Technical Department.

*****WARNING ON REQUIREMENTS: MINIMAL REQUIREMENT TO BE RESPECTED AT ALL TIMES.**